

Novodur® P2M-AT

ABS

INEOS Styrolution

Novodur® P2M-AT acrylonitrile butadiene styrene (ABS) polymer features high surface quality and good impact strength. Novodur® P2M-AT is a medium impact, high gloss injection molding grade with good flowability and contains an antistatic additive.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	20	cm³/10min	ISO 1133
Temperature	220	°C	-
Load	10	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Yield stress	39	MPa	ISO 527
Yield strain	2.1	%	ISO 527
Nominal strain at break	15	%	ISO 527
Impact Strength (Charpy), +23°C	180	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	120	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	22	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	11	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (1.80 MPa)	93	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	97	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	98	°C	ISO 306
Coeff. of Linear Therm. Expansion, parallel	100	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thicken.	HB	class	UL 94
Thickness tested	1.5	mm	-
UL recognition	yes	-	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	3.0	mm	-
UL recognition	yes	-	-

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Electric Strength	33	kV/mm	IEC 60243-1
Comparative tracking index	600	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1040	kg/m³	ISO 1183


Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Thermal Conductivity of Melt	0.127	W/(m K)	-
Spec. heat capacity of melt	1800	J/(kg K)	-
Ejection temperature	85	°C	-

Novodur® P2M-AT ABS


INEOS Styrolution

Diagrams


Viscosity-shear rate



Shearstress-shear rate



Specific volume-temperature (pvT)



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static

Injection Molding

PREPROCESSING

Pre-drying, Temperature: 80 °C

Pre-drying, Time: 2 - 4h

PROCESSING

Melt temperature, range: 230 - 260 °C

Mold temperature, range: 60 - 80 °C