

Hostalen ACP 9255 Plus (PE-HD)

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	12	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	21.6	kg	-

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	957	kg/m³	ISO 1183

Film Properties	Value	Unit	Test Standard
ISO Data			
Maximum stress, parallel	75	MPa	ISO 527-3
Maximum stress, normal	65	MPa	ISO 527-3
Maximum strain, parallel	450	%	ISO 527-3
Maximum strain, normal	470	%	ISO 527-3
Type of extrusion	blown	-	-
Thickness of specimen	0.02	mm	-

Characteristics

Processing

Blown Film Extrusion

Special Characteristics

Impact modified

Features

Good Drawdown, Low Gel

Chemical Resistance

Oxidation Resistance

Certifications

Food approval, Food approval 1935/2004/EC, Food approval 10/2011, Food Contact (FDA)

Applications

Packaging