

Hostalen CRP 100 W Blue (PE-HD)

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	0.27	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	5	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Yield stress	23	MPa	ISO 527
Yield strain	8	%	ISO 527
Tensile Creep Modulus, 1h	800	MPa	ISO 899-1
Tensile Creep Modulus, 1000h	350	MPa	ISO 899-1
Notched Impact Strength (Charpy), +23°C	26	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	13	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature, 50°C/h 50N	74	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	950	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding, Sheet Extrusion, Other Extrusion, Pipe/Tube Extrusion

Certifications

Food approval, Food approval 1935/2004/EC, Food approval 10/2011, Water contact

Chemical Resistance

Environmental Stress Crack Resistance