

Hostalen GF 7750 M3 (PE-HD)

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	0.6	g/10min	ISO 1133
MFI temperature	190	°C	-
MFI load	2.16	kg	-

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	135	°C	ISO 11357-1/-3

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	957	kg/m³	ISO 1183

Processing Recommendation Extrusion	Value	Unit	Test Standard
Zone 1	220 - 260	°C	-

Characteristics

Processing

Film Extrusion, Blown Film Extrusion

Features

Copolymer

Additives

Lubricants

Applications

Building Construction, Monofilament