

Durethan® BKV115 000000 DUS008 PA6-I-GF15

Envalior

Injection Molding, 15% Glass Reinforced, Improved Impact

ISO 1043 PA6-I-GF15

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	5600 / 2800	MPa	ISO 527
Stress at Break	115 / 65	MPa	ISO 527
Strain at Break	4 / 12	%	ISO 527
Impact Strength (Charpy), +23°C	65 / 80	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	50 / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	- / 15	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	- / 10	kJ/m ²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	195 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Density	1230 / -	kg/m ³	ISO 1183

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	260 - 290	°C	-
Mold temperature	80 - 100	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Impact modified

Delivery form

Pellets

Injection Molding

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 260 - 290 °C

Mold temperature: 80 - 100 °C