

Durethan® BKV30H2.0EF 901510 DUS029
PA6-GF30

Envalior

Injection Molding, 30% Glass Reinforced, Heat Stabilized, Improved flow

ISO 1043 PA6-GF30


Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.2 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577
Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9500 / 5500	MPa	ISO 527
Stress at Break	165 / -	MPa	ISO 527
Strain at Break	3 / -	%	ISO 527
Impact Strength (Charpy), +23°C	70 / -	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	55 / -	kJ/m ²	ISO 179/1eU
Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	90 / *	E-6/K	ISO 11359-1/-2
Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Density	1360 / -	kg/m ³	ISO 1183
Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80	°C	-
Pre-drying - Time	2 - 6	h	-
Processing humidity	≤0.12	%	-
Melt temperature	270 - 290	°C	-
Mold temperature	80 - 120	°C	-

Durethan® BKV30H2.0EF 901510 DUS029
PA6-GF30


Envalior

Diagrams


Stress-strain




Stress-strain



Secant modulus-strain




Secant modulus-strain




Durethan® BKV30H2.0EF 901510 DUS029
PA6-GF30

Envalior

Stress-strain (isochronous) 23°C



Creep modulus-time 23°C



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Heat aging stabilized

Injection Molding

PREPROCESSING

Residual moisture content: 0.03 - 0.12%

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer 2 - 6 h

PROCESSING

Melt temperature (Tmin - Tmax): 270 - 290 °C

Mold temperature: 80 - 120 °C