

Durethan BKV30XWPHV 000000

PA6-GF30

Envalior

PA 6, 30 % glass fibers, injection molding, improved weldability, heat-aging stabilized

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Molding shrinkage, parallel	0.3 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	9800 / 5600	MPa	ISO 527
Stress at Break	170 / 100	MPa	ISO 527
Strain at Break	3 / 8	%	ISO 527
Impact Strength (Charpy), +23°C	80 / 95	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	65 / 65	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	12 / 20	kJ/m²	ISO 179/1eA
Puncture - maximum force, +23°C	883 / -	N	ISO 6603-2
Puncture - maximum force, -30°C	791 / -	N	ISO 6603-2
Puncture energy, +23°C	3.4 / -	J	ISO 6603-2
Puncture energy, -30°C	2.8 / -	J	ISO 6603-2

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	200 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	215 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	20 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	100 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB / *	class	UL 94
Thickness tested	1.5 / *	mm	-
Burning Behav. at thickness h	HB / *	class	UL 94
Thickness tested	0.8 / *	mm	-
Oxygen index	23 / *	%	ISO 4589-1/-2

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	4.5 / 17	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.9 / 4.8	-	IEC 62631-2-1
Dissipation Factor, 100Hz	190 / 3900	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / >1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	* / 3.6E13	Ohm	IEC 62631-3-2
Electric Strength	32 / -	kV/mm	IEC 60243-1
Comparative tracking index	450 / -	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	6.5 / *	%	Sim. to ISO 62
Humidity absorption	2.3 / *	%	Sim. to ISO 62
Density	1360 / -	kg/m³	ISO 1183

Material Specific Properties	dry / cond	Unit	Test Standard
ISO Data			
Viscosity number	195 / *	cm³/g	ISO 307, 1157, 1628

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	280	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294

Characteristics

Durethan BKV30XWPHV 000000
PA6-GF30

Envalior

Processing

Injection Molding

Special Characteristics

Heat aging stabilized

Delivery form

Pellets

Injection Molding

PREPROCESSING

Residual moisture content: 0.03-0.12 %

Drying temperature dry air dryer: 80 °C

Drying time dry air dryer: 2-6 h

PROCESSING

Melt temperature (Tmin - Tmax): 270-290 °C

Mold temperature: 80-120 °C
