

**Durethan BTC75H3.0EF 900117**  
**PA6-MX75**

Envalior

ISO 16396-PA 6,MD75,GHR,S10-140

PA 6, 75% mineral, injection molding, heat-aging stabilized, improved heat conductivity

Rheological properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.6 / *	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7 / *	%	ISO 294-4, 2577

Mechanical Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	14700 / 6100	MPa	ISO 527
Stress at Break	90 / 50	MPa	ISO 527
Strain at Break	1.8 / 2.2	%	ISO 527
Impact Strength (Charpy), +23°C	28 / 26	kJ/m <sup>2</sup>	ISO 179/1eU
Impact Strength (Charpy), -30°C	18 / 11	kJ/m <sup>2</sup>	ISO 179/1eU

Thermal Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Melting Temperature (10°C/min)	221 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	160 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	200 / *	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	40 / *	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	40 / *	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / *	class	UL 94
Thickness tested	0.8 / *	mm	-

Electrical Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Volume Resistivity	>1E13 / -	Ohm*m	IEC 62631-3-1
Electric Strength	34 / 32	kV/mm	IEC 60243-1
Comparative tracking index	600 / -	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
<b>ISO Data</b>			
Water Absorption	2.5 / *	%	Sim. to ISO 62
Humidity absorption	0.8 / *	%	Sim. to ISO 62
Density	2290 / -	kg/m <sup>3</sup>	ISO 1183

**Characteristics**
**Processing**

Injection Molding

**Delivery form**

Pellets

**Special Characteristics**

Heat aging stabilized

**Features**

Thermally Conductivity