

Ultramid® B3L2 HP
PA6

BASF

Rheological properties	dry / cond	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	170 / *	cm ³ /10min	ISO 1133
Temperature	275 / *	°C	-
Load	5 / *	kg	-

Mechanical Properties	dry / cond	Unit	Test Standard
ISO Data			
Tensile Modulus	2700 / 1000	MPa	ISO 527
Yield stress	70 / 40	MPa	ISO 527
Yield strain	4 / 20	%	ISO 527
Nominal strain at break	10 / >50	%	ISO 527
Impact Strength (Charpy), +23°C	no break / no break	kJ/m ²	ISO 179/1eU
Impact Strength (Charpy), -30°C	no break / -	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	8 / 30	kJ/m ²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	6 / -	kJ/m ²	ISO 179/1eA

Thermal Properties	dry / cond	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	220 / *	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	180 / *	°C	ISO 75-1/-2

Electrical Properties	dry / cond	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	3.4 / 6	-	IEC 62631-2-1
Dissipation Factor, 1MHz	150 / 2500	E-4	IEC 62631-2-1
Volume Resistivity	1E13 / 1E10	Ohm*m	IEC 62631-3-1
Comparative tracking index	600 / -	-	IEC 60112

Other Properties	dry / cond	Unit	Test Standard
ISO Data			
Water Absorption	9 / *	%	Sim. to ISO 62
Humidity absorption	2.8 / *	%	Sim. to ISO 62
Density	1120 / -	kg/m ³	ISO 1183
Bulk density	700	kg/m ³	-

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	240 - 260	°C	-
Mold temperature	40 - 80	°C	-

Characteristics

Processing

Injection Molding

Special Characteristics

Impact modified

Delivery form

Pellets

Applications

Automotive, Building Construction, Electrical and Electronical