

Ultradur® B 4300 G6 FC Aqua
PBT-GF30

BASF

Ultradur® B 4300 G6 FC Aqua UN is suitable for plastic parts, where material approval regarding drinking water contact and direct food contact is a mandatory requirement.

The product is approved according to

- 21 CFR FDA §177.1660 "Poly(tetramethylene terephthalate)";
- European Food Contact European Food Contact Commission Regulation (EU) 10/2011;
- GMP (EC) N°2023/2006;

and suitable for drinking water contact in accordance with

- KTW-BWGL;
- WRAS (approval);
- ACS (disclosure of ingredients);
- NSF (disclosure of ingredients).

For questions regarding the compliance with further regulations, and certificates, please contact your local BASF representative or Plastics Safety (E-Mail: plastics.safety@basf.com).

The products can also be offered as BMBcert™ and/or Ccycled™. Due to the Massbalance approach the product properties do not change.

Abbreviated designation according to ISO 1043: PBT-GF30

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	11	cm³/10min	ISO 1133
Temperature	250	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	1.1	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	9800	MPa	ISO 527
Stress at Break	140	MPa	ISO 527
Strain at Break	3	%	ISO 527
Tensile Creep Modulus, 1000h	7500	MPa	ISO 899-1
Impact Strength (Charpy), +23°C	74	kJ/m²	ISO 179/1eU
Impact Strength (Charpy), -30°C	74	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	9	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy), -30°C	8.5	kJ/m²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	205	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	220	°C	ISO 75-1/-2
Coeff. of Linear Therm. Expansion, parallel	25	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion, normal	115	E-6/K	ISO 11359-1/-2
Burning Behav. at 1.5 mm Nom. Thickn.	HB	class	UL 94
Thickness tested	1.5	mm	-
UL recognition	yes	-	-
Burning Behav. at thickness h	HB	class	UL 94
Thickness tested	0.8	mm	-
UL recognition	yes	-	-
Oxygen index	19.5	%	ISO 4589-1/-2

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 100Hz	4	-	IEC 62631-2-1
Relative permittivity, 1MHz	3.8	-	IEC 62631-2-1
Dissipation Factor, 100Hz	25	E-4	IEC 62631-2-1

Ultradur® B 4300 G6 FC Aqua
PBT-GF30

BASF

Dissipation Factor, 1MHz	170	E-4	IEC 62631-2-1
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	1E13	Ohm	IEC 62631-3-2
Electric Strength	37	kV/mm	IEC 60243-1
Comparative tracking index	375	-	IEC 60112

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1530	kg/m³	ISO 1183

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	105	cm³/g	ISO 307, 1157, 1628

Rheological calculation properties	Value	Unit	Test Standard
ISO Data			
Density of melt	1300	kg/m³	-
Thermal Conductivity of Melt	0.22	W/(m K)	-
Spec. heat capacity of melt	1770	J/(kg K)	-
Ejection temperature	180	°C	-

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	260	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	60 - 100	°C	-

Ultradur® B 4300 G6 FC Aqua PBT-GF30


BASF

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Dynamic Shear modulus-temperature




Stress-strain




Ultradur® B 4300 G6 FC Aqua
PBT-GF30

BASF


Secant modulus-strain




Stress-strain (isochronous) 23°C



Creep modulus-time 23°C




Stress-strain (isochronous) 40°C




Ultradur® B 4300 G6 FC Aqua
PBT-GF30

BASF


Creep modulus-time 40 °C




Stress-strain (isochronous) 90 °C



Creep modulus-time 90 °C




Stress-strain (isochronous) 120 °C




Ultradur® B 4300 G6 FC Aqua
PBT-GF30

BASF


Creep modulus-time 120 °C




Stress-strain (isochronous) 160 °C



Creep modulus-time 160 °C



Specific volume-temperature (pvT)




Ultradur® B 4300 G6 FC Aqua


PBT-GF30

BASF

Tensile Modulus-Temperature



Coeff. of linear thermal expansion, normal



Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Lubricants

Special Characteristics

Light stabilized or stable to light, UV stabilized, Heat aging stabilized

Certifications

Food approval, Food approval 10/2011, Food Contact (FDA), Water contact, Water contact KTW, Water contact DVGW W270, NSF Approval

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %

Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C

Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 275 °C

injection molding, Melt temperature, recommended: 260 °C

injection molding, Mold temperature, range: 60 - 100 °C

injection molding, Mold temperature, recommended: 80 °C

Chemical Media Resistance

Acids

- ✓ Acetic Acid (5% by mass) (23°C)