

Ultradur® S 4090 G4X (PBT+ASA)-GF20

BASF

Low-warpage injection molding grade with 20 % glass fibres for technical parts, for which dimensional stability is very important (e.g. housings, plug-and-socket connectors).

Abbreviated designation according to ISO 1043: PBT-ASA-GF20

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	30	cm ³ /10min	ISO 1133
Temperature	275	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	0.5	%	ISO 294-4, 2577
Molding shrinkage, normal	0.9	%	ISO 294-4, 2577

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	6600	MPa	ISO 527
Stress at Break	100	MPa	ISO 527
Strain at Break	2.6	%	ISO 527
Impact Strength (Charpy), +23°C	49	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	5.5	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Melting Temperature (10°C/min)	223	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	185	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	210	°C	ISO 75-1/-2

Electrical Properties	Value	Unit	Test Standard
ISO Data			
Volume Resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface Resistivity	1E14	Ohm	IEC 62631-3-2
Electric Strength	39	kV/mm	IEC 60243-1

Other Properties	Value	Unit	Test Standard
ISO Data			
Water Absorption	0.4	%	Sim. to ISO 62
Humidity absorption	0.2	%	Sim. to ISO 62
Density	1390	kg/m ³	ISO 1183

Material Specific Properties	Value	Unit	Test Standard
ISO Data			
Viscosity number	104	cm ³ /g	ISO 307, 1157, 1628

Test specimen production	Value	Unit	Test Standard
ISO Data			
Injection Molding, melt temperature	270	°C	ISO 294
Injection Molding, mold temperature	80	°C	ISO 294
Injection Molding, injection velocity	200	mm/s	ISO 294


Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	80 - 120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.04	%	-
Melt temperature	250 - 275	°C	-
Mold temperature	60 - 100	°C	-

Ultradur® S 4090 G4X (PBT+ASA)-GF20


BASF

Diagrams


Dynamic Shear modulus-temperature




Stress-strain



Secant modulus-strain



Tensile Modulus-Temperature



Characteristics

Processing

Injection Molding

Special Characteristics

Light stabilized or stable to light, UV stabilized, Heat aging stabilized

Injection Molding

PREPROCESSING

Pre/Post-processing, max. allowed water content: .04 %

Ultradur® S 4090 G4X
(PBT+ASA)-GF20

BASF

Pre/Post-processing, Pre-drying, Temperature: 80 - 120 °C
Pre/Post-processing, Pre-drying, Time: 4 h

PROCESSING

injection molding, Melt temperature, range: 250 - 275 °C
injection molding, Melt temperature, recommended: 270 °C
injection molding, Mold temperature, range: 60 - 100 °C
injection molding, Mold temperature, recommended: 80 °C

Chemical Media Resistance

Acids

✓ Acetic Acid (5% by mass) (23°C)
