

Technical Data Sheet



ALTECH PP-B A 1000/310 IM

MOCOM

Base Polymer	Polypropylene Heterophasic Copolymer
Colour	natural color
Special Features	elastomer modified, impact modified, processing stabilised, heat stabilised
Market Segment	Automotive
Application Area	exterior parts, interior decoration / finishing, transport systems
Typical Applications	housings, functional components, fixing elements

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-240 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	800	MPa	ISO 178
Flexural Stress (3.5% Strain)	20	MPa	ISO 178
Tensile Modulus	850	MPa	ISO 527
Tensile Stress at Yield	20	MPa	ISO 527
Tensile Elongation at Yield	7.5	%	ISO 527
Impact Strength (Charpy, 23°C)	no break	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	75	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	52	°C	ISO 306
HDT / A (1,8 MPa)	50	°C	ISO 75-1/-2
DSC (Melt Point)	163	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	5	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	1.7 - 2.1	%	ISO 294-4
Shrinkage (lateral, 24h)	1.6 - 2	%	ISO 294-4
Physical Properties			
Density	900	kg/m ³	ISO 1183