

Technical Data Sheet



ALTECH PP-H A 3020/100 GB20

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	20 % glass beads
Colour	black,natural color
Special Features	heat stabilised,easy release (demoulding),processing stabilised
Market Segment	building and construction,Automotive,packaging
Application Area	injection moulded parts,exterior parts,clothing / fasteners,interior decoration / finishing
Typical Applications	housings,functional components

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	1700	MPa	ISO 178
Flexural Stress (3.5% Strain)	34	MPa	ISO 178
Tensile Modulus	1800	MPa	ISO 527
Tensile Stress at Yield	28	MPa	ISO 527
Tensile Elongation at Yield	7.7	%	ISO 527
Tensile Elongation at Break	43	%	ISO 527
Impact Strength (Charpy, 23°C)	38	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	10	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	3.5	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	2	kJ/m²	ISO 179/1eA
Thermal Properties			
Vicat B50	94	°C	ISO 306
HDT / A (1,8 MPa)	62	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	3	cm³/10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	0.7 - 0.9	%	ISO 294-4

Technical Data Sheet



ALTECH PP-H A 3020/100 GB20

MOCOM

Shrinkage (lateral, 24h)	1 - 1.2	%	ISO 294-4
--------------------------	---------	---	-----------

Physical Properties

Density	1030	kg/m ³	ISO 1183
---------	------	-------------------	----------