

Technical Data Sheet



ALTECH PP-H A 3020/500 GB20

MOCOM

Base Polymer	Polypropylene Homopolymer
Filler/Additive System	20 % glass beads
Colour	black,natural color
Special Features	easy release (demoulding),processing stabilised,heat stabilised
Market Segment	building and construction
Application Area	injection moulded parts,interior
Typical Applications	functional components,housings

Pre-Drying Conditions	in a dry air (dessiccant) dryer 80-120 °C for 2-3 h in an air circulating dryer 80-120 °C for 2-4 h dependant on moisture content max. moisture content <0,10 %
-----------------------	--

Processing Injection Moulding	melt temperature 200-250 °C mould temperature 20-70 °C
-------------------------------	---

Storage	dry, protected from light
---------	---------------------------

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Flexural Modulus	2000	MPa	ISO 178
Flexural Stress (3.5% Strain)	38	MPa	ISO 178
Tensile Modulus	2100	MPa	ISO 527
Tensile Stress at Yield	28	MPa	ISO 527
Tensile Elongation at Yield	6	%	ISO 527
Tensile Elongation at Break	25	%	ISO 527
Impact Strength (Charpy, 23°C)	27	kJ/m²	ISO 179/1eU
Impact Strength (Charpy, -40°C)	17	kJ/m²	ISO 179/1eU
Notched Impact Strength (Charpy, 23°C)	2.5	kJ/m²	ISO 179/1eA
Notched Impact Strength (Charpy, -40°C)	1.5	kJ/m²	ISO 179/1eA
Thermal Properties			
Vicat B50	100	°C	ISO 306
HDT / A (1,8 MPa)	65	°C	ISO 75-1/-2
DSC (Melt Point)	166	°C	ISO 11357
Rheological Properties			
Melt Index (MVR)	10	cm³/10min	ISO 1133
MVR temperature	230	°C	-
MVR load	2.16	kg	-
Shrinkage (lengthwise, 24h)	1.5 - 1.7	%	ISO 294-4
Shrinkage (lateral, 24h)	1.1 - 1.5	%	ISO 294-4
Physical Properties			
Density	1020	kg/m³	ISO 1183