

Moplen HF501N

PP HOMO

LyondellBasell Industries

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	10	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	1550	MPa	ISO 527
Yield stress	35	MPa	ISO 527
Yield strain	9	%	ISO 527
Strain at Break	>50	%	ISO 527
Notched Impact Strength (Charpy), +23°C	3	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Vicat softening temperature A	155	°C	ISO 306

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	900	kg/m ³	ISO 1183

Characteristics

Processing

Injection Molding

Delivery form

Pellets, Powder

Features

Homopolymer