

Purell HP570Z

PP HOMO

LyondellBasell Industries

Processing Method: Continuous Filament/Spinning; Fibers; Melt Blown.

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt Flow Index, MFI	1500	g/10min	ISO 1133
MFI temperature	230	°C	-
MFI load	2.16	kg	-

Characteristics**Processing**

Other Extrusion

Features

Barrier Properties, Homopolymer

Delivery form

Pellets