

ARBOFILL® Kokos

PP OTHERS

TECNARO GmbH

Rheological properties	Value	Unit	Test Standard
ISO Data			
Melt volume-flow rate, MVR	8	cm ³ /10min	ISO 1133
Temperature	190	°C	-
Load	2.16	kg	-
Molding shrinkage, parallel	1.0	%	Company Standard

Mechanical Properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2300	MPa	ISO 527
Tensile Strength	27	MPa	ISO 527
Stress at Break	27	MPa	ISO 527
Strain at Break	3	%	ISO 527
Impact Strength (Charpy), +23°C	16	kJ/m ²	ISO 179/1eU
Notched Impact Strength (Charpy), +23°C	5	kJ/m ²	ISO 179/1eA

Thermal Properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load (0.45 MPa)	104	°C	ISO 75-1/-2

Other Properties	Value	Unit	Test Standard
ISO Data			
Density	1000	kg/m ³	Company Standard

Characteristics

Processing

Injection Molding

Certifications

Contains renewable resources

Delivery form

Pellets, Brown