

**Moplen EP300R**  
 PP OTHERS

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index	30	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Density, 73°F	900	kg/m <sup>3</sup>	ASTM D 792

Mechanical Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	24	MPa	ASTM D 638
Elongation at Yield	5	%	ASTM D 638
Flexural Modulus	1050	MPa	ASTM D 790
Rockwell Hardness	R 85	-	ASTM D 785
Notched Impact Strength (Izod), 1/8 in	130	J/m	ASTM D 256
Notched Impact Strength (Izod), Low-Temperature	50	J/m	ASTM D 256
Temperature	-20	°C	-

Thermal Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	95	°C	ASTM D 648
Vicat Temperature	150	°C	ASTM D 1525

**Characteristics**
**Processing**

Injection Molding

**Special Characteristics**

Impact modified

**Features**

Copolymer, Impact Copolymer

**Applications**

Electrical and Electronical, Packaging