

Technical Data Sheet

❖ Alfater XL®



ALFATER XL A90E 2GP0000

MOCOM

Base Polymer	Thermoplastic Vulcanisate (PP+EPDM)
Colour	black
Service Temperature	max. range (depending on load, geometry, etc.) -40-125 °C
Special Features	high viscosity, good weathering resistance, good chemical resistance, good ozone resistance, good hot air resistance, good hydrolysis resistant
Market Segment	Automotive, building and construction, Machinery, electrical and electronic, Furniture
Application Area	extruded parts, blow moulded parts, coextrusion
Typical Applications	profile, seals, sealing lip, conduit, tubes, cable guides, cable jacketing, bellows, air duct, 2K components
Adhesion to	Polypropylene Homopolymer, Polypropylene Copolymer, Polyethylene, Thermoplastic Vulcanisate (PP+EPDM), Thermoplastic Olefin Elastomer, Thermoplastic Elastomer general
Approvals	PMR

Pre-Drying Conditions	in a dry air (dessiccant) dryer 70-80 °C for 2-4 h max. moisture content <0,10 %
Processing Extrusion	melt temperature 190-230 °C die temperature 190-220 °C
Storage	dry, protected from light tightly sealed

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile Stress at 100% Elongation (Type 2)	6.6	MPa	ISO 37
Tensile Strength (Type 2)	14.5	MPa	ISO 37
Tear Strength (Method Ba)	55	kN/m	ISO 34-1
Elongation at Break (Type 2)	550	%	ISO 37
Shore Hardness A (15s)	90	-	ISO 868
Thermal Properties			
Coeff. of Linear Therm. Expansion (parallel)	12.9	E-6/K	ISO 11359-1/-2
Coeff. of Linear Therm. Expansion (normal)	16.5	E-6/K	ISO 11359-1/-2
Compression Set (22h / 100 °C / 25% / Type A)	58	%	ISO 815
Compression Set (22h / 70 °C / 25% / Type A)	50	%	ISO 815
Compression Set (72h / 22 °C / 25% / Type A)	32	%	ISO 815
Compression Set (72h / 125 °C / 25% / Type A)	80	%	ISO 815
Electrical Properties			
Surface Resistance	1E12	Ohm	DIN EN 62631-3-2

Technical Data Sheet

Alfater XL®

ALFATER XL A90E 2GP0000




MOCOM

Tracking Resistance (CTI)	600	-	IEC 60112
Physical Properties			
Density	950	kg/m ³	ISO 1183
Ageing Properties			
Ozone resistance (method A)	passed	-	ISO 1431-1A
Flammability			
Glow Wire (GWFI, 650°C, 2.0mm)	passed	-	DIN EN 60695

Diagrams

Stress-Strain



Dynamic Shear modulus-temperature

