

Acetal Copolymer KEPITAL®

TE-24S

- POM

Grade

			KEPITAL TE-24S
	ASTM D792	—	1.32
23 , 60%RH	ASTM D570	%	0.25
190 , 2.16 kg	ASTM D1238	g/10min	2.5
10 /min	ASTM D3418		165
4.6kg _f /cm ²	ASTM D648		77
18.6kg _f /cm ²			13
20 80	ASTM D696	10 ⁻⁵ cm/cm/	HB
t 0.8mm	UL94	—	
23	ASTM D638	kg _f /cm ²	360
23	ASTM D638	%	300<
23	ASTM D790	kg _f /cm ²	415
23	ASTM D790	kg _f /cm ²	12,700
Izod t 3.2mm	ASTM D256	kg _f • cm/cm	NB
10 ⁶ Hz	ASTM D150	—	-
10 ⁶ Hz	ASTM D150	—	-
	ASTM D257	Ω	1 10 ¹⁶
	ASTM D257	Ω • cm	1 10 ¹⁴
	ASTM D149	kV/mm	-
(//) t 2mm, Φ 100mm		%	1.3

) 1.

2.