

LG CHEM LTD 20 YOIDO-DONG YONGDUNGPO-GU SEOUL, 150-721 Republic of Korea



LM915, LM915H

Acrylonitrile Butadiene Styrene (ABS)/Acrylonitrile Styrene Acrylate (ASA), pellets

Flammability	Value	Test Method
Flame Rating		
1.5 to 3.0 mm, ALL	НВ	UL 94
1.5 to 3.0 mm, ALL	HB75	IEC 60695-11-10, -20
Electrical	Value	Test Method
Hot-wire Ignition (HWI) (1.5 to 3.0 mm)	PLC 4	UL 746
High Amp Arc Ignition (HAI) (1.5 to 3.0 mm)	PLC 0	UL 746
Comparative Tracking Index (CTI)	PLC 0	UL 746
Dielectric Strength	21 kV/mm	ASTM D149
High Voltage Arc Tracking Rate (HVTR)	PLC 2	UL 746
Volume Resistivity	1.0E+14 ohms·cm	ASTM D257 IEC 60093
Arc Resistance	PLC 6	ASTM D495
Thermal	Value	Test Method
RTI Elec (1.5 to 3.0 mm)	50.0 °C	UL 746
RTI Imp (1.5 to 3.0 mm)	50.0 °C	UL 746
RTI Str (1.5 to 3.0 mm)	50.0 °C	UL 746

Page 1 of 1 Form Number: E67171-103749121

Report Date: 6/26/2018 Last Revised: 10/7/2019 8:43:51 PM

UL and the UL logo are trademarks of UL LLC Copyright © 2021 All Rights Reserved. | www.ul.com