

GND45

Description

Neodymium catalyst Linear polymer

Application

Golf Ball, Shoe Sole, Tire

Key Features

Abrasion Resistance, Fuel Efficiency

Properties	Condition	Unit	GND45	Method
Polymer Property				
Organic Acid		wt %	Max 1.0	ASTM D5774
Volatile Material		wt %	Max 0.7	ASTM D5668
Extractable		wt %	Max 2.0	ASTM D5774
Ash		wt %	Max 0.3	ASTM D5667
Cis		%	Min 96.0	LG Method
Polymer Viscosity	ML1+4,100°C	MU	45±5	ASTM D1646

Precaution

It should be stored in warehouse to be protected from sunlight, heat and moisture.

Shelf life : 24 month from date of production at room temperatures not exceeding 30°C under above storage condition (Retest critical parameters like MV and others after the expiry of shelf life)

Package

35kg bale, 35kg X 36bales = 1.26MT box