

# EA28150

## Description

Excellent compatibility with other raw material of HMA  
Good organoleptic property

## Application

Hot Melt Adhesive

Properties	Method	Condition	Unit	EA28150
Physical				
VA Contents	LG Method		%	28
Density	ASTM D1505	Density-Gradient	g/cm <sup>3</sup>	0.946
MFI	ASTM D1238	190°C, 2.16kg load	g/10min	150
Mechanical				
Tensile Strength at break point	ASTM D638	50mm/min	kgf/cm <sup>2</sup>	4.5
Elongation at break point	ASTM D638	500mm/min	%	900
Hardeness(Shore A)	ASTM D2240	Shore A		74
Thermal				
Melting Temperature	LG Method	by DSC	°C	70

## Note

The properties data in this table are typical values, and not guaranteed specification.  
Typical resin property values are measured on a standard compression molded specimens.

## Storage and handling Recommendations

Ethylene Vinyl Acetate Copolymers are available in free-flowing pelletized form designed for use in conventional polymer fabrication systems.  
Ethylene Vinyl Acetate Copolymer storage and handling of these product is extremely important for the products to remain flowable for transport and processing without pellet blocking.

- To minimize static load, do not double stack pallets.
- Keeping storage and handling temperature between 10 ~ 25°C.
- Store the resins in the warehouse to protect from exposure to elevated temperature which is not to exceed 35°C.
- Consume the resins on a first in, first out basis.