

ES28005

Ethylene Vinyl Acetate Copolymer

Applications

- Foam compounds

Performance

- Uniform VA Contents and MI
- Strict contaminants control
- Excellent additives acceptance
- High shock absorption for shoes

Typical properties

Characteristics	Test Method	Unit	Value
Physical⁽¹⁾			
VA Contents	LG	%	28
Density	ASTM D1505	g/cm ³	0.951
MFR(190°C,2.16Kg)	D1238	g/10min	5
Mechanical⁽²⁾			
Tensile Strength at Break	D638 ⁽³⁾	Mpa	12
Elongation at Break	D638 ⁽³⁾	%	800
Hardness			
Shore hardness(Shore A)	D2240	-	79
Thermal			
Melting Temperature	LG	°C	72

(1) The properties data in this table are typical values, and not guaranteed specification.

(2) Typical resin property values are measured on a standard compression molded specimens

(3) Speed of 500 mm/min.

Processing information

- **ES28005** may be processed on conventional equipment.

ES28005

Ethylene Vinyl Acetate Copolymer

Storage and handling Recommendations

Ethylene Vinyl Acetate Copolymers are available in free-flowing pelletized form designed for use in conventional polymer fabrication systems.

Ethylene Vinyl Acetate Copolymer storage and handling of these product is extremely important for the products to remain flowable for transport and processing without pellet blocking.

- **To prevent pellet blocking**
 - To minimize static load, do not double stack pallets.
 - Keeping storage and handling temperature between 10 ~ 25°C.
 - Store the resins in the warehouse to protect from exposure to elevated temperature which is not to exceed 35°C.
 - Consume the resins on a first in, first out basis.