

LF100A

Description

EOR(Ethylene-1-Octene copolymer)
For POP(Polyolefin Plastomer) film

Application

Lamination film, Packaging Films

Properties	Method	Condition	Unit	LF100A
Physical				
MFI	ASTM D1238	190°C, 2.16kg load	g/10min	1.2
Density	ASTM D1505	Density-Gradient	g/cm ³	0.902
Color(Yellow Index)	LG Method			1.4
Film Properties				
Tensile Strength at Break Point, MD	ASTM D882	500mm/min	kgf/cm ²	49
Tensile Strength at Break Point, TD	ASTM D882	500mm/min	kgf/cm ²	46
Elongation at Break Point, MD	ASTM D882	500mm/min	%	540
Elongation at Break Point, TD	ASTM D882	500mm/min	%	630
Elmendorf Tear Strength, MD	ASTM D1922	500mm/min	gf/μm	11.5
Elmendorf Tear Strength, TD	ASTM D1922	500mm/min	gf/μm	15.5
Puncture Resistance	ASTM D4833		J/cm ³	5.2
Haze(50μm)	ASTM D1003	50μm	%	3.5
Thermal				
Melting Temperature	LG Method	by DSC	°C	98

Note

The properties data in this table are typical values, and not guaranteed specification.
Typical film property values are measured on 50μm single layer blown film specimens(BUR 2.3).