

WIC PP 30 N; BK; BKD

(Stand: 21.05.2021)

Base Polymer	Polypropylene
Filler	30% carbon fiber
Colour	Natur (carbon look), black, deep black
Special Features	heat aging stabilized
Typical Applications	automotive, sport

Pre Drying Conditions	circulation-air dryer 80°C for 2-4h, dependant on moisture content max. moisture content <0,10%
Processing Conditions	injection moulding melt temperature 210-260°C injection moulding mould temperature 30-60°C Under certain circumstances, the thermal conductivity has to be considered.
Storage	dry, protected from light

Properties	Value	Dimension	Test Norm
Mechanical Properties			
Tensile modulus	13000	MPa	ISO 527-1/-2
Tensile strength	93	MPa	ISO 527-1/-2
Tensile elongation at break	3,5	%	ISO 527-1/-2
Flexural modulus	12000	MPa	ISO 178
Flexural strength	140	MPa	ISO 178
Charpy Impact strength unnotched 23°C	52	kJ/m ²	ISO 179/1eU
Charpy Impact strength unnotched -40°C	-	kJ/m ²	ISO 179/1eU
Charpy Impact strength notched 23°C	10	kJ/m ²	ISO 179/1eA
Charpy Impact strength notched -40°C	-	kJ/m ²	ISO 179/1eA
Thermal Properties			
Vicat B50	125	°C	ISO 306
HDT/A (1,8 MPa)	154	°C	ISO 75-1/-2
Melt Point (DSC)	166	°C	ISO 11357
Electrical properties			
Surface resistance max.	10	Ohm	IEC 62631-3-2
Specific volume resistance	11	Ohm*cm	IEC 62631-3-1
Rheological Properties			
MVR	6	cm ³ /10min	ISO 1133
MVR temperature	230	°C	-
MVR load	5	kg	-
Shrinkage - lengthwise	0,1	%	ISO 294-4
Shrinkage - lateral	0,4	%	ISO 294-4
Physical Properties			
Density	1070	kg/m ³	ISO 1183

WIC PP 30 N; BK; BKD

(Stand: 21.05.2021)

CO₂-Footprint (GWP100)

1,26

[kg CO₂ eq.]

**GaBi (DIN EN ISO
14040/14044)**

These are guide values and not a specification. The test values mentioned are representative values only and not binding minimum or maximum figures. These test values have been determined on standardized test specimens and can be affected by pigmentation, mould design and processing conditions.

Any information given on the chemical and physical characteristics of our products, including, without limitation, technical advice on applications, whether verbally, in writing or by testing the product, is given to the best of our knowledge and in good faith and does not exempt the buyer from carrying out their own investigations and tests in order to ascertain the product's specific suitability for the purpose intended. The buyer is solely responsible for confirming the suitability of the product for a particular application, its utilization and processing and must observe any applicable laws and government regulations.

NO EXPRESS OR IMPLIED RECOMMENDATION OR WARRANTY IS GIVEN WITH REGARD TO THE SUITABILITY OF THE PRODUCT FOR A PARTICULAR APPLICATION, SUCH AS, BUT NOT LIMITED TO; SAFETY-CRITICAL COMPONENTS OR SYSTEMS.

Important: Irrespective of product type or designation, WIPAG does not recommend or support the use of any products it supplies which fall in the following medical, pharmaceutical or diagnostic application categories.

- risk class III applications according to EU directive 93/42/EEC
- any bodily implant applications for greater than 30 days
- any critical component in any medical device that supports or sustains human life.

At all times, our standard terms and conditions of sale apply.