



TAITALAC 1000

ABS Resin

DESCRIPTION

- Injection
- Medium high impact
- Good flow for process
- High gloss

APPLICATION

- Computer / TV / telephone housing
- Toy and furniture components
- Extrusion film
- Office equipment
- Kitchen appliances
- House-ware
- Battery
- Shoes

Properties	Test	Test Condition	SI unit		English unit	
			Unit	s.p.	Unit	s.p.
Specific Gravity	ASTMD792			1.03		
Melt Flow Index	ASTMD1238	200°C , 5kg load	g/10min	1.6		
Melt Flow Index	ASTMD1238	220°C , 10kg load	g/10min	16		
Mechanical						
Izod Impact Strength	ASTMD256	23°C , 1/4 in notched	kg-cm/cm	23	ft-lb/in	4.2
Izod Impact Strength	ASTMD256	23°C , 1/8 in notched	kg-cm/cm	25	ft-lb/in	4.6
Tensile Strength at Yield	ASTMD638	23°C , 1/8 in, 5 mm/min	kg/cm ²	400	psi	5700
Tensile Strength at Break	ASTMD638	23°C , 1/8 in, 5 mm/min	kg/cm ²	350	psi	5000
Elongation at Break	ASTMD638	23°C , 1/8 in, 5 mm/min	%	30		
Flexural Yield	ASTMD790	23°C , 2.8 mm/min	kg/cm ²	700	psi	10000
Flexural Modulus	ASTMD790	23°C , 2.8 mm/min	kg/cm ²	24000	psi	340000
Thermal						
Heat Distortion Temperature	ASTMD648	Unannealed, 1/2 in, 18.56 kg/cm ² load pressure	°C	84	°F	180
Vicat Softening Temperature	ASTMD1525	1/8 in , 1 kg load	°C	97	°F	212
Physical						
Rockwell Hardness	ASTMD785	23°C , R-scale	R-scale	110		
Mold Shrinkage	ASTMD955		%	≤0.4		
Water Absorption	ASTMD570		wt %	≤0.3		
Flammability	UL-94	1/16 in	File No E50263	HB		
Electrical						
Relative Temperature Index	UL-746B	0.062 in above	°C	60	°F	140
Hot Wire Ignition	UL-746A	0.062 in above	Secs	17		
High Current Arc Ignition	UL-746A	0.062 in above	Arcs	200		
Arc Tracking Rate	UL-746A	0.062 in above	in/min	0		

Note : The data listed represent average values and are believed to be reliable. They are given for information; no guarantee of their accuracy is made.