Application/Uses

- Films
- Flexible Packaging
- Disposable Gloves
- IV Containers
- Wound care

Key Attributes

- Good adhesion or compatibility to various substrates
- Good heat and RF sealing
- Low temperature toughness
- Soft, flexible, tough without plasticizers

Product Description

Westlake EBAC® SP1802 is a 22.5% EBA copolymer designed for blown film, tie-layer, coextrusions and blending where flexibility and strength are important. SP1802 provides excellent elasticity and low temperature performance.

Typical Physical Properties		
<u>Property</u> ^a	Test ^b Method	<u>Typical Value, Units^c</u>
Melt Index (Condition 190°C/2.16 kg)	D 1238	0.5 g/10 min
Density	D 1505	927 kg/m³ (0.927 g/cm³)
Vicat Softening Temperature	D 1525	59°C (138°F)
Butyl Acrylate Content		22.5%
Melting Point by DSC	D 3418	86°C (187°F)
Brittleness Temperature	D 746	<-73°C (<-99°F)
Durometer Hardness Shore D Scale	D 2240	40
Tensile Stress @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	13 MPa (1823 psi)
Elongation @ Break 500 mm/min (20 in./min)	D 638 Type IV Specimen	848%

Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

NOTES

EBAC resins adhere to and are compatible with a wide range of materials including paper, polyolefins, oriented polyolefins, polyesters, ionomers, PVC, unplasticized PVC and other polar polymers. For use as heat seal layer, adhesive layer, or modifier for cost/performance enhancement. They are soft, pliable and tough at ambient and freezing temperatures and exhibit excellent ESCR. These polymers exhibit high solids fillability and compatibility with a wide range of polymers. This facilitates their uses as bases for all-purpose concentrates for addition to a wide spectrum of polymers. They process like LDPE.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Processing conditions for EMAC and EBAC resins will vary depending on application, fabrication equipment, and other resinuse. For assistance with applications and temperature profiles, contact the Westlake Technical Services Department at

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatumentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.