

Westlake Chemical

ELEVATETM

EF446
6.0% EVA Copolymer

Application/Uses

- High Clarity Packaging
- Foam Applications

Product Description

Westlake EF446 resin is a 6.0% EVA copolymer designed for general purpose packaging film. This Kosher compliant resin has excellent clarity, toughness, heat sealing characteristics, low temperature brittleness properties, and machinability.

Typical Physical Properties			
<u>Property</u> ^a		Test ^b Method	Typical Value, Units ^c
Melt Index (Condition 190°C/2 Density Haze (Base Polymer) Gloss @ 45° (Base Polymer) Impact Tensile Strength @ Break	2.16 kg) M.D. T.D. M.D.	D 1238 D 1505 D 1003 D 2457 D 1709A D 882 D 882 D 882 D 882	2.0 g/10 min 927 kg/m³ (0.925 g/cm³) 4.3% 73 % 180 g 30 MPa (4495 psi) 26 MPa (3950 psi) 440%
1% Secant Modulus	T.D. M.D. T.D.	D 882 D 882 D 882	770% 109 MPa (16300 psi) 127 MPa (19100 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

NOTES

Kosher Compliant. Test specimens for blown film: nominal thickness 1.25 mils; blow up ratio 2.5:1, die gap 35 mils.

FDΔ

This resin grade complies with 21 CFR 177.1350. For further information, please contact Product Regulatory Compliance.

PROCESSING

Melt temperatures of 360° F – 390° F are recommended for Westlake Chemical EF446 with blow-up ratios of 1.5:1 or higher.

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

^b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.