ELEVATETM
EF598
9.0 % EVA copolymer

Application/Uses

- Food packaging tie layer
- Heat seal layer
- Extrusion coating and cast film
- Compounding

Product Description

Westlake EF598 resin is a 9.0% EVA copolymer designed for extrusion coating, laminations, cast film, and compounding. This grade exhibits excellent clarity, toughness, drawdown, and TD heat shrinkage.

Typical Physical Properties^a

<u>Property</u>	Test Method ^b	Typical Value, Units
Melt Index Density Peak Melting Temperature Durometer Hardness, Shore D Vicat Softening Temperature Tensile at Break	D 1238 D 1505 D 3417 D 2240 D 1525 D 638 Type IV	8.0 g/10 min 930 kg/m³ (0.930 g/cm³) 207°F (97°C) 48 165°F (74°C) 11.8MPa (1,760 psi)
Tensile at Yield Elongation at Break Tensile Modulus, 1% Secant	D 638 Type IV D 638 Type IV D 822	6.9 MPa (1,030 psi) 500% 93 MPa (14,000 psi)

^aUnless noted otherwise, all tests are run at 73°(23°C) and 50% relative humidity.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Extrusion melt temperatures of $380^{\circ} - 420^{\circ}$ F are recommended for EF598.

NOTICE

The data listed represents typical values as measured by Westlake. They are given for information only, and not guarantee of their accuracy is made. The product is sold upon condition that purchasers shall make their own tests to determine the characteristics of the product and the suitability of the product for their particular purpose.

Westlake makes no representation or warranty of any kind, express or implied, with respect to this product, whether as to merchantability, fitness for particular purpose or otherwise.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

^bUnless noted otherwise, the test method is ATM.