



台達通用及耐衝擊聚苯乙烯

TAITAREX GPPS/HIPS

通用聚苯乙烯(General Purpose Polystyrene) GPPS 866N / B

特性

Characteristics

- | | |
|---|--|
| <ul style="list-style-type: none"> ● 射出級 ● NOVA CHEMICAL 最新生產技術 ● 低殘留單體量 ● 耐熱性佳 ● 表面尺寸安定性佳 ● 優異透明度 ● 良好加工性 ● 電器性佳 | <ul style="list-style-type: none"> ● Injection Grade ● The most state of the art from US NOVA CHEMICAL ● Low Residual Monomer ● Good Heat Resistance ● Mold Dimension Stability ● Good Transparency ● Easy Processing ● Good Electrical Properties |
|---|--|

應用

Applications

CD-Case/Slim、家電製品、家庭五金、化妝品容器等。 CD-Case/Slim, electrical appliances, house hardwares, cassette & cosmetic cases.

物理性質 Physical Properties

Properties	Test Method	Test Condition	Unit	Typical Value
比重 Specific Gravity	ASTM D792	23℃	---	1.046
	ISO 1183		g/cm ³	1.04
流動指數 Melt Flow Index	ASTM D1238	200℃, 5 kg load	g/10min	5.0
	ISO 1133		ml/10min	5.3
抗張強度 Tensile Strength at Yield	ASTM D638	23℃, 1/8" Sample	kg/cm ²	450
	ISO 527		Mpa	44
伸長率 Elongation at Break	ASTM D638	23℃, 1/8" Sample	%	2.0
	ISO 527			
Izod 耐衝擊強度 Izod Impact Strength	ASTM D256	23℃, A method, notched 1/4"×1/2"×5/2"	kg-cm/cm	1.4
	ISO 180A	23℃ Notched	KJ/m ²	1.8
Vicat 軟化溫度 Vicat Softening Temperature	ASTM D1525	1 kg load, 3 mm Thick(120℃/hr)	℃	100
	ISO 306	1 kg load, 3 mm Thick(50℃/hr)		98
燃燒性 Flammability	UL-94	1/16" Sample	File No. E50263	94HB
殘留苯乙烯單體 Residual SM monomer	---	---	ppm	200
曇度 Haze	---	2.8mm thick	%	0.4

註：上表所列數據依據 ASTM 試驗方法所測得，僅供參考用。

Note : The data listed represent average values and are believed to be reliable. They are given for information; no guarantee of their accuracy is made.