



WPP PP PPC1GF2UV-RXF

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight		
Additive	• UV Stabilizer		
Features	• Copolymer • Good Dimensional Stability	• Good Stiffness • High Tensile Strength	• UV Resistant
Uses	• Consumer Applications	• Industrial Applications	
Appearance	• Colors Available		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.80	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	55.0	MPa	ISO 527-2/5
Flexural Modulus ²	3400	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	13	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	122	°C	ISO 75-2/A

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min