



WPP PP PPC1TF1.3 848 Black

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

General			
Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Talc, 13% Filler by Weight		
Features	• Copolymer	• Good Stiffness	• High Tensile Strength
Uses	• Automotive Applications		
Appearance	• Black	• Colors Available	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	0.70	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	29.0	MPa	ISO 527-2/50
Flexural Modulus ²	2080	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength (23°C)	24	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	100	°C	ISO 75-2/B

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min