



WPP PP PPC2935-Natural

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

Product Description

Properties shown below for a medium melt flow copolymer polypropylene.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Features	• Copolymer • Good Processing Stability	• Good Stiffness • High Impact Resistance	• Medium Flow
Uses	• Automotive Applications	• Automotive Interior Trim	
Appearance	• Colors Available	• Natural Color	
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.898	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	32	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	29.0	MPa	ASTM D638
Flexural Modulus	1500	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	56	J/m	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D)	74		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 0.45 MPa, Unannealed	118	°C	ASTM D648

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min