



WPP PP PPC2CF7-Natural-UV

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Calcium Carbonate, 72% Filler by Weight		
Additive	• UV Stabilizer		
Features	• Copolymer	• Medium Flow	• UV Resistant
Uses	• Consumer Applications	• Industrial Applications	
Appearance	• Colors Available		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Flexural Modulus ²	4500	MPa	ISO 178

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 13 mm/min