



WPP PP PPC2MF1.3-Black

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

Product Description

Properties shown below for this filled blend are typical for a 13% mica reinforced polypropylene copolymer. This product satisfies many application needs. Special compounds are available.

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Mica, 13% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Copolymer	• Heat Stabilized	• High Heat Resistance
Uses	• Automotive Applications		
Appearance	• Black	• Colors Available	
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.978	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	25.0	MPa	ASTM D638
Flexural Modulus ³	2100	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	68	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 1.8 MPa, Unannealed	70.0	°C	ASTM D648

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 50 mm/min

³ 1.3 mm/min