

## WPP PP PPC3GF1.5-Black

## Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information					
Product Description					
Properties shown below for this f	filled blend are typical for a15% fiberglas	s reinforced polypropylene copolyme	er.		
General					
Material Status	Commercial: Active				
Availability	<ul><li>Africa &amp; Middle East</li><li>Asia Pacific</li></ul>	<ul><li>Europe</li><li>Latin America</li></ul>	North America		
Filler / Reinforcement	Glass Fiber, 15% Filler by Weight				
Additive	<ul> <li>UV Stabilizer</li> </ul>				
Features	<ul><li>Copolymer</li><li>Good Stiffness</li></ul>	<ul><li>High Tensile Strength</li><li>Medium Flow</li></ul>	UV Resistant		
Appearance	Black	<ul> <li>Colors Available</li> </ul>			
Forms	<ul> <li>Pellets</li> </ul>				

ASTM & ISO Properties 1				
Physical	Nominal Value	Unit	Test Method	
Density / Specific Gravity	0.982	g/cm³	ASTM D792	
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0	g/10 min	ASTM D1238	
Mechanical	Nominal Value	Unit	Test Method	
Tensile Strength <sup>2</sup> (Yield)	33.8	MPa	ASTM D638	
Flexural Modulus <sup>3</sup>	1570	MPa	ASTM D790	
Flexural Strength <sup>3</sup>	46.2	MPa	ASTM D790	
Impact	Nominal Value	Unit	Test Method	
Notched Izod Impact (23°C)	210	J/m	ASTM D256	
Thermal	Nominal Value	Unit	Test Method	
Deflection Temperature Under Load			ASTM D648	
0.45 MPa, Unannealed	147	°C		
Deflection Temperature Under Load			ASTM D648	
1.8 MPa, Unannealed	87.0	°C		

## Additional information

our control, and we cannot and will not take responsibility for the information or content.

## Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.



Tested at  $23 \pm 2$ °C ( $73.4 \pm 3.6$ °F) and  $50 \pm 5$ % relativehumidity unless otherwise noted

<sup>&</sup>lt;sup>2</sup> 51 mm/min

<sup>&</sup>lt;sup>3</sup> 5.3 mm/min