



WPP PP PPC4TF1.3-Black

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Talc, 13% Filler by Weight		
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Copolymer • High Scratch Resistance	• Low Gloss • Medium Heat Resistance	• UV Resistant
Uses	• Automotive Interior Parts		
Appearance	• Black	• Colors Available	

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	18	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	25.0	MPa	ISO 527-2/50
Tensile Stress (Break)	25.0	MPa	ISO 527-2/50
Flexural Modulus ²	1600	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength			ISO 180
-40°C	3.0	kJ/m ²	
-15°C	3.5	kJ/m ²	
23°C	5.0	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (0.45 MPa, Unannealed)	118	°C	ISO 75-2/B
Heat Deflection Temperature			
1.8 MPa, Unannealed	64.0	°C	ISO 75-2/A
1.8 MPa, Unannealed	60.0	°C	ISO 75-2/Af

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted.

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min