



WPP PP PPC6TF1V-RXF

Washington Penn Plastic Co. Inc. - Polypropylene Copolymer

Wednesday, October 9, 2019

General Information

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
Filler / Reinforcement	• Talc, 10% Filler by Weight		
Features	• Copolymer	• High Flow	
Uses	• Automotive Applications		
Appearance	• Colors Available		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.970	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	31.0	MPa	ISO 527-2/50
Flexural Modulus ²	1700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	63.0	°C	ISO 75-2/A

Additional Information

Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 5% relative humidity unless otherwise noted

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 mm/min