

WPP PP PRC25TF3.2-Black

Washington Penn Plastic Co. Inc. - Polypropylene Homopolymer

Wednesday, October 9, 2019

General Information				
Commercial: Active				
 Africa & Middle East Asia Pacific	EuropeLatin America	North America		
 Talc, 32% Filler by Weight 				
 Heat Stabilizer 				
• Yes, 25%				
 Heat Stabilized 	 Homopolymer 	 Low Halogen Content 		
 Automotive Applications 	Automotive Under the Hood			
Black	Colors Available			
	 Commercial: Active Africa & Middle East Asia Pacific Talc, 32% Filler by Weight Heat Stabilizer Yes, 25% Heat Stabilized Automotive Applications 	Commercial: Active Africa & Middle East Asia Pacific Talc, 32% Filler by Weight Heat Stabilizer Yes, 25% Heat Stabilized Automotive Applications Europe Latin America Europe Heatin America Hatin America Heatin America Hatin A		

ASTM & ISO Properties 1					
Physical	Nominal Value	Unit	Test Method		
Density	1.16	g/cm³	ISO 1183		
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min	ISO 1133		
Mechanical	Nominal Value	Unit	Test Method		
Tensile Stress (Yield)	28.0	MPa	ISO 527-2/5		
Tensile Strain (Yield)	7.0	%	ISO 527-2/5		
Flexural Modulus - Tangent ²	3100	MPa	ISO 178		
Impact	Nominal Value	Unit	Test Method		
Notched Izod Impact Strength			ISO 180		
-40°C	2.0	kJ/m²			
23°C	3.0	kJ/m²			
Thermal	Nominal Value	Unit	Test Method		
Heat Deflection Temperature (0.45 MPa, Unannealed)	129	°C	ISO 75-2/B		
Heat Deflection Temperature (1.8 MPa, Unannealed)	83.0	°C	ISO 75-2/A		

Additional Information	
Tested at $23 \pm 2^{\circ}$ C (73.4 ± 3.6°F) and $50 \pm 5\%$ relative humidity unless otherwise noted.	

Notes

¹ Typical properties: these are not to be construed as specifications.



² 2.0 mm/min