

# **Sicoflex<sup>®</sup> MZ341 225230**

ABS

Industrial Quality Compound

## **Description:**

ABS general purpose, medium flow

## **General**

MFI (220°C/10kg)	ISO 1133	16	g/10min
------------------	----------	----	---------

## **Thermal**

HDT/A (1,82MPa)	ISO 75A	91	°C
Vicat softening point (B50 (50N))	ISO 306	97	°C

## **Mechanical**

Izod notched impact strength (23°C)	ISO 180	12	kJ/m <sup>2</sup>
Tensile stress at yield	ISO 527	40	MPa
Elongation at break	ISO 527	25	%
Flex modulus	ISO 178	2500	MPa

The data and information contained herein are typical average values, based on our current level of knowledge and experience, and do not constitute sales specifications. No liability, warranty or guarantee of product performance is created by this document. Ravago industrial quality compounds are totally or partially produced with non-prime quality ingredients. Even though the selection of the raw materials, the production and the quality control is being done following to the common best practices, it is the buyer's responsibility to inspect and test our products in order to determine the suitability for the buyer's application.

## **Ravago Group Headquarters**

Moerenstraat 85A  
B - 2370 Arendonk

Tel: +32 (0)14 67 25 11  
Fax: +32 (0)14 67 20 12

www.ravago.com  
manufacturing@ravago.com

Issue Date:  
Sep 2016