

## Processing Guidelines

### TPE-40IP321- (Any Color)

#### Pressures

Injection	700 - 1400 psi
Holding	150 - 750 psi
Back	075 - 150 psi

#### Injection Speed

0.75 - 2.5 in/s

#### Temperatures

• Barrel Zone 1	340-380 °F
• Barrel Zone 2	340-380 °F
• Barrel Zone 3	350-390 °F
• Barrel Zone 4	350-390 °F
• Nozzle	360-400 °F
• Hot Runner	360-400 °F
• Mold	60-130 °F
• Hydraulic Oil Temperature	110-125 °F

*Material Drying is typically not required but for some thin walled parts drying may be required.  
If needed dry at 160 – 190°F for 1-2 hours.*

#### Machine/Shot Information

Shot Capacity vs. Barrel Capacity	2.5 to 4.0
Cushion	1/8" to 1/4"
Screw Decompression	0.10" to 0.25"
Clamp Tonnage should be 2.5 to 4.0 Tons per square inch of projected part area.	