

Website www.washpenn.com

# **TPO-3975 UVP 848 GLM**

Polyolefin Alloy - Weather Resistant, 1700 MPa Flexural Modulus, High Flow

### **TYPICAL APPLICATIONS:**

Exterior fully-painted applications such as bumper fascias, rockers, bodysides and fascia accents

### **Features and Options:**

- Tested at  $23 \pm 2$ °C ( $73.4 \pm 3.6$ °F) and  $50 \pm 5$ % relative humidity unless otherwise noted. Excellent balance of impact strength and rigidity.
- Very good ductility and practical toughness.
- **UV** Stabilized
- Paintable Compound

## **Product Description:**

Properties shown below are typical for a 20% mineral filled thermoplastic olefin alloy. Additional products are offered with properties tailored for specific applications

Approved to: GMP.E/P.157 **GMW15188** 

| Physical Properties                    | Typical Values*        | Test Method |
|--|------------------------|-------------|
| Melt Flow                              | 24 g/10 min            | ISO 1133    |
| Filler Content                         | 20%                    | ISO 3451    |
| Density                                | 1.03 g/cm <sup>3</sup> | ISO 1183    |
| Notched Izod Impact @ 23°C             | 54 kJ/m <sup>2</sup>   | ISO 180     |
| Notched Izod Impact @ -30°C            | 7 kJ/m <sup>2</sup>    | ISO 180     |
| Tensile Strength @ Yield (50mm/minute) | 15 MPa                 | ISO 527     |
| Flexural Modulus (2mm/minute)          | 1,700 MPa              | ISO 178     |
| Deflection Temperature @ 1820 KPa      | 52°C                   | ISO 75      |
| Multiaxial Impact @ 23°C               | 17 J                   | ASTM D3763  |
| Multiaxial Impact @ -30°C              | 20 J                   | ASTM D3763  |

NOTE: Custom colors available upon request.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.

<sup>\*</sup> Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Washington Penn Plastic representative.