# EC474 Low Density Polyethylene

### Application/Uses

- Medium and lightweight coatings and laminations
- Substrate coatings to provide heat sealability
- Hot melt laminating adhesive
- General purpose coatings

## **Product Description**

WESTLAKE low-density polyethylene EC474 is a general-purpose formulation used for extrusion coating and laminating. It can be drawn down to low coating weights, is processable at high speeds, has good moisture barrier, and is heat-sealable at low temperatures.

## Typical Physical Properties

Property	Test Method	Typical Value, Units
Melt Index	D 1238	8.0 g/10 min
Density	D 1505	918 kg/m³ (0.918 g/cm³)
Ultimate Tensile	D 638	1,400 psi
Elongation	D 638	400 %
Tensile Modulus	D 1709	20,000 psi

<sup>&</sup>lt;sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

## NOTES

Where required, test specimens are compression molded according to ASTM D1928.

#### **FDA**

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

#### **PROCESSING**

Westlake EC474 has very good flow properties which allow high speed coatings at weights from 4 lbs/3000 sq. ft. and up. Melt temperatures of 575° F - 625° F are suggested for Westlake EC474.

#### COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

b Unless noted otherwise, the test method is ASTM.

<sup>&</sup>lt;sup>c</sup> Units are in SI or US customary units.