



WASHINGTON PENN PLASTIC CO INC
2080 N MAIN ST EXT, PO BOX 236, WASHINGTON PA 15301-0236



UP6X303(f3)(f4), UP6X305(f3)(f4),

Polypropylene (PP), pellets, glass reinforced

- (f3) - Suitable for use with respect to exposure to detergents, bleach and solutions typically used in fluid containing parts of laundry equipment, in accordance with UL 2157
(f4) - Suitable for use with respect to exposure to aqueous dishwasher detergent solution and/or rinse agent solution in accordance with UL 749.

Flammability	值	测试方法
Flame Rating		
1.5 mm, ALL	HB	UL 94
3.0 mm, ALL	HB	UL 94
3.0 mm, ALL	HB40	IEC 60695-11-10, -20
1.5 mm, ALL	HB75	IEC 60695-11-10, -20
Glow Wire Flammability Index (1.5 mm)	750 °C	IEC 60695-2-12
Glow Wire Ignition Temperature (1.5 mm)	750 °C	IEC 60695-2-13
Electrical	值	测试方法
Hot-wire Ignition (HWI) (1.5 mm)	PLC 3	UL 746
High Amp Arc Ignition (HAI) (1.5 mm)	PLC 0	UL 746
Comparative Tracking Index (CTI)	PLC 0	UL 746
Dielectric Strength	51 kV/mm	ASTM D149 IEC 60243-1
Volume Resistivity	1.0E+12 ohms-cm	ASTM D257 IEC 60093
Thermal	值	测试方法
RTI Elec		UL 746
1.5 mm	120 °C	
3.0 mm	125 °C	
RTI Imp		UL 746
1.5 mm	120 °C	
3.0 mm	125 °C	
RTI Str		UL 746
1.5 mm	120 °C	
3.0 mm	125 °C	

Notice of Disclaimer

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.