

HDPE for LiBS Seperator

YUHWHA HIDDEN VH035

Features
and Uses

Properties

Contact
Info.

Application	HDPE for LiBS Seperator			
Features	Good property & Processibility balance			
Uses	LiBS of wet process (Lithium 2nd Battery Separator)			
Items	Specification	Unit	Test Method	
Average Mv (10 ⁶ g/mol)	0.6	—	KPIC Method	
Density	0.95	g/cm ³	ASTM D1505	
Bulk Density	0.46	g/cm ³	ISO 60	
Avg. Particle Size	125	μm	KPIC Method	
Melting Point	135	℃	ASTM D3418	
※ Above data are intended to serve as guides only, and are not sales specification limits.				
Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr