

HDPE for LiBS Seperator

YUHWA HIDDEN VH150U

- Features
and Uses
- Properties
- Contact
Info.

Application	HDPE for LiBS Seperator			
Features	Good property & Processibility balance			
Uses	LiBS of wet process (Lithium 2nd Battery Separator)			
Items		Specification	Unit	Test Method
Average Mv (10 ⁶ g/mol)		1.5	—	KPIC Method
Density		0.94	g/cm ³	ASTM D1505
Bulk Density		0.46	g/cm ³	ISO 60
Avg. Particle Size		125	μm	KPIC Method
Melting Point		135	℃	ASTM D3418
※ Above data are intended to serve as guides only, and are not sales specification limits.				
Division	Team in charge	TEL	FAX	e-mail
International Trade	KPICC	82-2-3706-0844, 0849	82-2-3706-0893, 0894	trade@kpicc.com
Technical Service	Marketing Support Team	82-2-2122-1537	82-2-2122-1519	H15106@kpic.co.kr