

## **WPP351-Natural**

An unfilled injection molding grade polypropylene copolymer

## **TYPICAL APPLICATIONS:**

Various

## **Product Description:**

The properties shown below are typical for a high impact polypropylene copolymer. This basic product satisfies the needs of many applications.

Approved To: MS-DB500 CPN 4919, CPN 4017

MS.50042 MS-DB500 CPN 5182

WSS-M4D638-C

## **Features and Options:**

- · High melt flow for filling large parts
- · Good balance of stiffness and impact strength
- Tested at 23 ± 2°C (73.4 ± 3.6°F) and 50 ± 10% relative humidity unless otherwise noted.

| 1166 III-2666 G                          |                        |             |
|--|------------------------|-------------|
| Physical Properties                      | Typical Values*        | Test Method |
| Melt Flow                                | 20 g/10min             | ISO 1133    |
| Density                                  | 0.89 g/cm <sup>3</sup> | ISO 1183    |
| Notched Izod Impact @ 23°C               | 42 kJ/m²               | ISO 180     |
| Notched Izod Impact @ -40°C              | 6 kJ/m²                | ISO 180     |
| Notched Charpy Impact @ 23°C             | 45 kJ/m²               | ISO 179     |
| Tensile Strength @ Yield (50mm/minute)   | 18 MPa                 | ISO 527     |
| Tensile Elongation @ Yield (50mm/minute) | 5%                     | ISO 527     |
| Tensile Modulus (1mm/minute)             | 970 MPa                | ISO 527     |
| Flexural Modulus (2mm/minute)            | 900 MPa                | ISO 178     |
| Deflection Temperature @ 1820 KPa        | 51°C                   | ISO 75      |

NOTE: Custom colors available upon request.

The results reported are typical and based on reliable testing procedures. However, due to variable processing methods and conditions, no guarantees or warranties are expressed or implied, including expressions of fitness for purpose or merchantability. No recommendations are made to infringe on patents.

<sup>\*</sup> Values given are typical and should not be interpreted as product specification. To obtain values for specific application purposes, contact your Washington Penn Plastic representative.