Application/Uses

- Converter film for food
- Flexible medical
- Industrial packaging

Product Description

Westlake Polyethylene EN1817 is a low density formulation suggested for film applications requiring high clarity, good tear and impact strength, good printability and a wide heat-sealing range.

Typical Physical Properties			
Property ^a		Test ^b Method	<u>Typical Value, Units^c</u>
Melt Index (Condition 190°C Density Haze Gloss @ 45° Impact Tensile Strength @ Break Elongation (%) 1% Secant Modulus	/2.16 kg) M.D. T.D. M.D. T.D. M.D. T.D.	D 1238 D 4883 D 1003 D 2457 D 1709A D 882	1.7 g/10 min 920 kg/m³ (0.920 g/cm³) 6.0% 70 110 g 34 MPa (4900 psi) 23 MPa (3200 psi) 300% 850%
1% Secant Modulus	M.D. T.D.	D 882 D 882	207 MPa (30000 psi) 240 MPa (35000 psi)

^a Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

NOTES

Test specimens for blown film: nominal thickness 1.5 mils; blow up ratio 2.4:1, die gap 50 mils.

FDA

This product has some 21 CFR clearances. Please contact Westlake Product Regulatory Department for statements.

PROCESSING

Melt temperatures of 360° F – 380° F are recommended for Westlake EN1817 with blow-up ratios of 2.4:1 or higher.

COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

b Unless noted otherwise, the test method is ASTM.

^c Units are in SI or US customary units.