# EC4041 Low Density Polyethylene

# Application/Uses

Food-contact applications

# **Product Description**

WESTLAKE low-density polyethylene EC4041 is recommended for use in the boardstock coating industry. The resin has low neck-in and good drawdown characteristics. Coatings produced from EC4041 have excellent heat-sealing characteristics.

Typical Physical Properties			
Property <sup>a</sup>		Test <sup>b</sup> Method	Typical Value, Units <sup>c</sup>
Melt Index (Condition 190°C/2.16 kg) Density		D 1238 D 4883	5.6 g/10 min 922 kg/m <sup>3</sup> (0.922 g/cm <sup>3</sup> )
Tensile Stress @ Break Elongation @ Break Flexural Modulus	500 mm/min (20 in./min) 500 mm/min (20 in./min) (2% Secant) 12.7 mm/min (0.5 in./min)	D 638 Type IV D 638 Type IV D 790	13.1 MPa (1900 psi) 180% 255 MPa (37,000 psi)

<sup>&</sup>lt;sup>a</sup> Unless noted otherwise, all tests are run at 23°C (73°F) and 50% relative humidity.

## **NOTES**

Kosher Compliant. Where required, test specimens are compression molded according to ASTM D1928.

#### FD4

This resin grade complies with 21 CFR 177.1520. For further information, please contact Product Regulatory Compliance.

## **PROCESSING**

Melt temperatures of 575° F - 625° F are recommended for Westlake Chemical EC4041.

#### COMMENTS

Properties reported here are based on limited testing. Westlake makes no representation that the material in any particular shipment will conform exactly to the values given.

Westlake and its marketing affiliates shall not be responsible for the use of this information, or of any product, method, or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability of fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

## **WESTLAKE CHEMICAL CORPORATION**

2801 Post Oak Blvd Suite 600 Houston, Texas Customer Service: 1-800-545-9577

b Unless noted otherwise, the test method is ASTM.

<sup>&</sup>lt;sup>c</sup> Units are in SI or US customary units.